

// 753AA



**Sandblast 12 bar (180 psi) - Premium quality**

**Tube:** black conductive NR - abrasion resistance 50 mm<sup>3</sup> (ISO 4649/A).

**Reinforcement:** high tensile textile cords.

**Cover:** black SBR/NR - abrasion and ozone resistant - pin pricked.

**Application:** abrasive material blasting.

Designed for long service life in heavy duty applications.

**Constant operation:** -40 °C +80 °C (-40 °F +176 °F)

↔		↔		↙	↘	↻		↵		⚖		
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
13,0	1/2"	27,00	1,06	12	180	36	540				0,540	0,37
19,0	3/4"	33,00	1,30	12	180	36	540				0,700	0,48
19,0	3/4"	38,00	1,50	12	180	36	540				0,990	0,67
19,0	3/4"	40,00	1,57	12	180	36	540				1,150	0,78
25,0	1"	39,00	1,54	12	180	36	540				0,860	0,58
25,0	1"	48,00	1,89	12	180	36	540				1,520	1,03
32,0	1 1/4"	48,00	1,89	12	180	36	540				1,220	0,82
32,0	1 1/4"	55,00	2,17	12	180	36	540				1,810	1,22
38,0	1 1/2"	55,00	2,17	12	180	36	540				1,630	1,10
38,0	1 1/2"	60,00	2,36	12	180	36	540				2,050	1,38
51,0	2"	71,00	2,80	12	180	36	540				2,380	1,60
51,0	2"	73,00	2,87	12	180	36	540				2,640	1,78
51,0	2"	76,00	2,99	12	180	36	540				2,910	1,96

// 755AA



**Sandblast 12 bar (180 psi) - Top quality**

**Tube:** black conductive NR - abrasion resistance 36 mm<sup>3</sup> (ISO 4649/A).

**Reinforcement:** high tensile textile cords.

**Cover:** black SBR/NR - abrasion and ozone resistant - pin pricked.

**Application:** abrasive material blasting.

Designed for long service life in heavy duty application.

**Constant operation:** -40 °C +80 °C (-40 °F +176 °F)

↔		↔		↙	↘	↻		↵		⚖		
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
19,0	3/4"	33,00	1,30	12	180	36	540				0,740	0,50
25,0	1"	39,00	1,54	12	180	36	540				0,910	0,62
32,0	1 1/4"	48,00	1,89	12	180	36	540				1,280	0,87
38,0	1 1/2"	55,00	2,17	12	180	36	540				1,470	0,99
51,0	2"	71,00	2,80	12	180	36	540				2,430	1,64